



81

1762

PATENTIN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

TREVOR HAMILTON et al.

Serial No.: RCE of 09/599,174

Filing Date: June 22, 2000

Title: FOULING INHIBITION

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Docket: ACC 0786 P1US

Examiner: Jolley, Kirsten

Group Art Unit: 1762

CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the United States Postal Service as First-Class mail in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450

on October 7, 2003


Lynn Brush

RECEIVED

OCT 29 2003

TC 1700

Enclosed herewith is a certified copy of United Kingdom Application No. 9727261.1, to support the claim of foreign priority benefits under 35 U.S.C. §119 in connection with the above-identified application.

Respectfully submitted,



Lainie E. Parker
Attorney for Applicant(s)
Reg. No. 36,123

Akzo Nobel Inc.
Intellectual Property Dept.
7 Livingstone Avenue
Dobbs Ferry, NY 10522-3408
(914) 674-5466

1918
JAN 10
RECEIVED
U.S. DEPT. OF JUSTICE

RECEIVED

JAN 10

U.S. DEPT. OF JUSTICE



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

RECEIVED
OCT 29 2003
TC 1700

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Stephen Hordley

Dated 24 September 2003





23 DEC 1997

29DEC97 E327008-1 C12278
P01/7700 25.00 - 9727261.1

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference

AJC/BK IP/A12/VALKYRIE/3347

2. Patent application number

(The Patent Office will fill in this part)

9727261.1

3. Full name, address and postcode of the or of each applicant (underline all surnames)

COURTAULDS COATINGS (HOLDINGS) LIMITED
50 George Street
London
W1A 2BB

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

9627906002
United Kingdom

4. Title of the invention

"Fouling Inhibition"

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

ABEL & IMRAY

Northumberland Ho 20 Red Lion Street
303-306 High Holb LONDON
London WC1V 7LH WC1R 4PQ

Patents ADP number (if you know it)

174 001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

Yes

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description

28 / *AN*

Claim(s)

4 /

Abstract

1 /

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

1 / *AN*

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11. ☒ We request the grant of a patent on the basis of this application.

Signature

Date

A. J. Coulson

23rd December 1997

12. Name and daytime telephone number of person to contact in the United Kingdom

A. J. Coulson

0171-242 9984

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

DUPLICATE

IP/A12/VALKYRIE

COURTAULDS COATINGS (HOLDINGS) LIMITED

FOULING INHIBITION

ABEL & IMRAY

Northumberland House,

303-306 High Holborn,

London.

WC1V 7LH

AJC/BK

23rd December 1997

IP/A12/VALKYRIE

FOULING INHIBITION

5 This invention relates to a process for inhibiting fouling of a substrate in a fouling environment, more especially a marine or other aquatic environment.

Man-made structures such as boat hulls, buoys, drilling platforms, oil production rigs and pipes which are immersed in water are prone to fouling by aquatic organisms such as green and brown algae, barnacles, mussels and the like. Marine structures are commonly of metal, but may also comprise other structural materials such as concrete. For smaller boats, the hulls may instead comprise, for example, wood or a fibre-reinforced resin. This fouling is a nuisance on boat hulls, because it increases the frictional resistance towards movement through the water, with the consequence of reduced speeds and increased fuel costs. It is a nuisance on static structures such as the legs of drilling platforms and oil production rigs, firstly because the resistance of thick layers of fouling to waves and currents can cause unpredictable and potentially dangerous stresses in the structure, and, secondly, because fouling makes it difficult to inspect the structure for defects such as stress cracking and corrosion. It is a nuisance in pipes such as cooling water intakes and outlets, because the effective cross-sectional area is reduced by fouling, with the consequence of reduced flow rates.

The commercially most successful methods of inhibiting fouling have involved the use of anti-fouling coatings containing substances toxic to aquatic life, for example tributyltin chloride or cuprous oxide. Such coatings, however, are being regarded with increasing disfavour because of the damaging effects such toxins can have if released into the aquatic environment. There is accordingly a need for non-fouling coatings which do not contain markedly toxic materials.

It has been known for many years, for example, as disclosed in GB 1 307 001 and US 3 702 778 that silicone rubber coatings resist fouling by aquatic organisms. It is believed that such coatings present a surface to which the organisms cannot easily adhere, and they can accordingly be called non-fouling rather than anti-fouling coatings. Silicone rubbers and silicone compounds generally have very low toxic properties. Silicone rubber coatings have, however, gained little commercial acceptance. It is difficult to make them adhere well to the substrate surface that is to be protected, and they are mechanically rather weak and liable to damage.

EP 0 032 597 discloses that silicone polymers onto which organic polymeric segments are grafted may be vulcanised to form non-fouling coatings. The vulcanisation procedure may utilise a crosslinking agent such as tetraethyl orthosilicate and a catalyst such as a tin salt.

GB 2 188 938 discloses that vinylic polymers containing polymeric silicone side chains may be used to form thermoplastic non-fouling coatings.

GB Patent Application 2 192 400 discloses anti-fouling paint compositions which comprise a vinylic copolymer obtained by copolymerisation of:

- (a) 1-50% by weight of a polymerisable unsaturated polysiloxane compound;
- (b) 0-30% by weight of a polymerisable unsaturated alkoxysilane compound; and
- (c) 20-99% by weight of a polymerisable unsaturated vinyl monomer other than (a) or (b).

The disclosed anti-fouling paint compositions may also comprise a hydroxyalkyl-tipped poly(diorganosiloxane) to the extent of 1-50 parts by weight per 100 parts by weight of the vinylic copolymer. The vinylic copolymer and the poly(diorganosiloxane) are not curable one with the other, and the coatings disclosed in GB-A-2 192 400

are thermoplastic and not vulcanised.

Coatings which contain a chemically inert oil or grease, often called a slipping agent, have been reported to offer improved resistance to fouling. GB 1 470 465
5 discloses the use of silicone oils as slipping agents in a vulcanised silicone rubber formulation. GB 1 581 727 discloses the use of silicone-free organic compounds, for example polyolefins with a molecular weight up to about 5000, as slipping agents in a vulcanised silicone rubber
10 formulation.









WO 93/13179 discloses a composition for fouling inhibition which comprises (A) a functional-group containing polymer having no more than a minor proportion of siloxane repeating units and (B) a polysiloxane which
15 is curable with the polymer (A). After application of the composition to a substrate and curing, the innermost region of the resulting coating generally comprises no more than a minor proportion of siloxane material whereas the coating presents a siloxane-rich surface layer to the
20 external environment. As a result, the coating provides fouling inhibition properties whilst at the same time the problems of mechanical weakness of previously proposed silicone rubber coatings are alleviated or avoided.

The present invention provides a process for
25 inhibiting the fouling of a substrate in a fouling environment, which comprises forming on the substrate, before exposure to the said environment, a coating comprising a film-forming polymer (A) carrying unreacted silicon-containing functional groups providing latent
30 reactivity, and thereafter applying a layer comprising a curable polysiloxane (B) and bonding the applied layer to the said coating by a condensation curing reaction involving the unreacted functional groups thereon.

The invention further provides a substrate bearing a
35 coating which has been applied by the process, i.e., having an outer layer comprising cured component (B).

An especially important aspect of the present invention comprises inhibition of fouling of structures in aquatic and, in particular, marine environments, especially the hulls of boats and ships of all sizes.

The condensation curing reaction between the silicon-containing functional groups and the curable polysiloxane may proceed, for example, as follows:



may hydrolyse to an aldehyde or ketone, $\text{R}'\text{R}^2\text{CO}$ and hydroxylamine, NH_2OH , under the conditions of the condensation.


The film-forming polymer (A) may comprise pendant and/or terminal curable functional groups. Pendant curable functionality is preferred, for example, in the case where the polymer is derived from one or more ethylenically unsaturated monomers, and terminal curable functionality is preferred, for example, if the polymer (A) is polyurethane, epoxy or polyester based.

The silicon-containing curable groups may be mono-, di- or tri-functional. In the case of di- or tri-functional groups, it is in general not necessary to

provide a separate cross-linking agent for the curing reaction with the polysiloxane (B).

Advantageously, the curable silicon-containing groups are curable by virtue of one or more curable functional groups selected from aliphatic, aromatic and araliphatic ether (for example, methoxy) and oxime groups. Although the silicon-containing functional groups can in principle be curable by virtue of ester groups, there may be difficulties in obtaining the desired period of latency in the case of ester groups comprising relatively short-chain hydrocarbon moieties (say, up to C₃ or C₄).


Preferably, the curable silicon-containing functional groups are groups of the formula



in which the groups represented by R₁, R₂ and R₃ may be the same or different and each may comprise an ether or ester group, preferably a group including a straight-chain or branched alkyl moiety having from 1 to 4 carbon atoms, and in which one or two of R₁ to R₃ may represent hydrogen or a hydrocarbon group, preferably a straight-chain or branched alkyl group having from 1 to 4 carbon atoms.

Examples of preferred silicon-containing functional groups are trimethoxy silyl and methyl dimethoxysilyl.

Other preferred silicon-containing functional groups comprise one or more oxime groups of the formula -



in which R⁴ and R⁵ may be the same or different and each represents a straight-chain or branched, saturated or unsaturated, aliphatic hydrocarbon radical, preferably having up to 7 carbon atoms, more especially up to 4 carbon atoms, especially a methyl or ethyl group; an aromatic group, for example, a phenyl group; or an

araliphatic group, for example, a benzyl group; or R^4 and R^5 together represent an alkylene group; or one of R^4 and R^5 represents hydrogen. Preferably each of R^4 and R^5 is other than an aromatic group. A group R^4 and/or R^5 may
5 be substituted or unsubstituted.

Preferably, the silicon-containing functional groups do not contain any amine functionality, and preferably also no silanol functionality; each of those functionalities tends to detract from the desired latent
10 reactivity.

Preferably, the film-forming polymer does not contain any functional groups apart from those conferring the desired latent reactivity. If any other functional groups are present, care must be taken to ensure that
15 such additional groups do not detract from the desired latent reactivity. Examples of functional groups which may interfere in this way are acid functionalities and amine and other base functionalities. Such interfering groups should be avoided both in the film-forming polymer
20 and in the coating formulation used to apply the polymer.

Preferably, pendant curable silicon-containing functional groups in (A) are connected to the polymer by a chemical linkage that is resistant to aqueous hydrolysis in natural waters; sea water, for example, has
25 pH 8.0-8.3. The silicon-containing bonds which are capable of undergoing condensation curing as described above, for example silyl ether and silyl ester, are therefore generally unsuitable for the purpose of attaching silicon-containing groups to the polymer back-
30 bone. It is preferred that the said chemical linkage should contain silicon directly linked to carbon. For example, the chemical linkage may comprise an alkylene group C_nH_{2n} where n is a non-zero integer preferably having the value 1-5, an alkylidene group, or an arylene
35 group, for example phenylene, or may be a direct chemical bond to a carbon atom in the polymer backbone.

The film-forming polymer may be derived from one or more ethylenically unsaturated monomers, more especially from one or more ethylenically unsaturated monomers selected from unsaturated aliphatic hydrocarbons, for example, ethylene, propylene and butylene; unsaturated halogenated hydrocarbons, for example, vinyl chloride, vinyl fluoride, vinylidene chloride and vinylidene fluoride; vinyl aromatic compounds, for example, vinyl pyridine, vinyl naphthalene, and styrene (including ring-substituted styrenes); unsaturated esters, amides and nitriles; and N-vinyl compounds, for example, N-vinyl pyrrolidone, N-vinyl carbazole and N-vinyl caprolactam. Mention should also be made of polyvinylacetate and polyvinylalcohol.



As further possibilities, the film-forming polymer may comprise repeating units derived from urethanes, ureas, urethane-ureas, amides, imides, amide-imides, epoxy compounds, and esters. Mention should also be made of alkyl resins and polyethers.

As particular examples of olefinic monomers may be mentioned such compounds as acrylic and methacrylic esters, amides and nitrile derivatives, styrene and vinyl chloride. Acrylate and methacrylate esters are preferred monomers, especially those derived from saturated alcohols containing 4-16 carbon atoms, such as the butyl, hexyl, octyl, decyl, dodecyl and hexadecyl esters. Mention should also be made of isobornyl acrylate and isobornyl methacrylate.

Advantageously, the polymer of (A) is derived from one or more monomers (A1) which carry curable silicon-containing groups and one or more monomers (A2) which do not carry such groups. In the case of monomer(s) (A1) carrying pendant curable silicon-containing groups, the molar proportion of monomer(s) (A1) to that of monomer(s) (A2) may be in the range of from 5% to 25%, typically at least 8% or 12% and usually not exceeding 20%. The

preferred range is dependent principally on the nature of the latent functional groups, the latency period desired, and the nature of the polymer backbone.

5 Polymers (A) carrying curable silicon-containing groups may expediently be manufactured by the polymerization of one or more monomers containing such groups, advantageously with one or more comonomers which do not contain such groups. For example, such silicon-containing monomers may be derivatives of compounds such
10 as acrylic acid, methacrylic acid, styrene, or ethylene. Examples of derivatives of acrylic and methacrylic acid are the esters in which the esterifying group includes the said silicon-containing group. As particular examples of such derivatives there may be mentioned 3-
15 (trimethoxysilyl)propyl acrylate and methacrylate (I) and 3-(dimethyl(trimethoxysilyloxy)silyl)propyl acrylate and methacrylate (II) (Me represents =methyl).



20 Compound I(R represents CH_3) is particularly preferred ("TMSPM").

25 Examples of derivatives of styrene as monomers (A1) are those in which a benzene ring is substituted both with a vinyl or 2-propenyl group and with a silicon-containing group. As particular examples of styrene derivatives there may be mentioned the isomeric trimethoxysilylstyrenes and the isomeric 2-(trimethoxysilyl-
30 ethyl)styrenes. As examples of derivatives of ethylene as monomers (A1) may be mentioned trimethoxyvinylsilane and triethoxyvinylsilane.

35 Instead of using monomers (A1) which already carry curable silicon-containing groups, it is possible (but less preferred) to graft such groups, for example trimethoxysilyl groups, onto a preformed polymer carrying

suitable reactive sites at which the curable silicon-containing groups can be attached.

Thus, for example, trimethoxysilyl and methyl dimethoxysilyl functional groups may be incorporated by
5 reaction of the corresponding mercaptopropyl silane with epoxy groups.

It may also be advantageous to utilise two or more different comonomers not containing a curable silicon group, for example a C₁₋₄ alkyl acrylate or methacrylate
10 ester together with a C₆₋₁₆ acrylic or methacrylic ester. Thus, for example, in another preferred embodiment, polymer (A) is derived from the following monomers in the following molar proportions:

	TMSPM		10%
15	Lauryl or butyl acrylate	20%)	
)	90%
	Methyl methacrylate	70%)	

The following general considerations are relevant in determining a suitable composition for the film-forming
20 polymer having unreacted functional groups conferring latent reactivity:

- i) Increasing the content of functional groups will generally increase the cost of the polymer material and will tend to decrease its storage stability,
25 but tends to increase the period of latency when the polymer material has been applied to the substrate.
- ii) The T_g of the polymer should be above room temperature and, in general, increasing T_g will lead to improved barrier performance of the coating and
30 to an extended period of latency. It may be noted, however, that if the T_g is too high there may be interference with the subsequent curing reaction with the polysiloxane, although the effect of this
35 can in principle be reduced by increasing the content of silicon-containing functional groups. It will be appreciated that the T_g of the polymer can be varied by suitable choice of monomers and

monomer proportions.

5 iii) The preferred minimum content of silicon-
containing functional groups in the polymer (A) in
the initial coating formulation will depend, inter
10 alia, on the reactivity of the groups concerned.
Thus, for example, trimethoxysilyl groups will tend
to be more reactive than methyl dimethoxysilyl
groups, and each will tend to be more reactive than
the corresponding propoxy groups (which will
15 normally be isopropoxy groups).

Although the film-forming polymer may include a
proportion of siloxane repeating units, at least a major
proportion of the repeating units, and preferably at
least 55% of the units, are other than siloxane units.

15 The proportion of siloxane repeating units is advanta-
geously not more than 25%, preferably not more than 10%,
and more especially not more than 5%. In a preferred
form of composition, the polymer of component (A) is
substantially free of siloxane repeating units.

20 The film-forming polymer may have a number-average
molecular weight in the range of from 1 000 to 50 000,
preferably up to 15 000, more especially from 3000 to
10 000.

25 If appropriate, a chain transfer agent may be used
in the production of the film-forming polymer (A). As
examples of chain transfer agents there may be mentioned
1-dodecanethiol and mercapto- propyltrimethoxysilane.
The molecular weight of the polymer may also be
controlled by varying the content of polymerisation
30 initiator. Examples of preferred free-radical initiators
include organic peroxides such as tert-butyl peroxy-2-
ethylhexanoate (available under the trade name Trigonox
215) and the materials available under the trade names
Trigonox 27 and Trigonox 41-C 75.

35 It will be appreciated, from the requirement for the
initial coating to have unreacted functional groups

providing latent reactivity, that the initial coating formulation should not include any cross-linking agent or curing catalyst, nor indeed any other material which may detract unduly from the desired latency (for example, acids, bases, organic metal salts, water or other protic solvents). The initial coating should be formulated so as to behave generally as a thermoplastic material during the period of latency, with only a minimum of self-curing taking place. The initial film formation takes place by solvent evaporation rather than by a curing reaction.

The practical minimum period of latency will depend in turn on the desired or necessary minimum interval between application of the initial coating and subsequent application of the curable polysiloxane. In general it is considered that a minimum latency period of 2 hours under the prevailing conditions will be needed, but there will be circumstances requiring a minimum of 12, 24 or 48 hours, a week, a month or even longer. Factors influencing the latency period have been outlined hereinbefore.

The latency period for any given coating can be determined using a standard overcoating test under specified conditions of temperature and humidity. Test portions of the curable polysiloxane material are applied at a series of different time intervals to different test areas of an initially coated substrate and cured onto the initial coating. The latency period is identified as the maximum time interval (after application of the initial layer) at which satisfactory adhesion of the polysiloxane coating is still achieved.


In practical operation, the polysiloxane coating can be applied at any time before expiry of the latency period for the initial coating used.

The or each curable polysiloxane applied according to the invention to the initial coating having latent reactivity may be an organohydrogenpolysiloxane or a

polydiorganosiloxane. The polysiloxane may, for example, comprise a copolymer of diorganosiloxane units with organohydrogen siloxane units and/or with other diorganosiloxane units, or a homopolymer of organohydrogen siloxane units or of diorganosiloxane units.

Subject to curability with the unreacted silicon-containing functional groups of the initial coating, the curable polysiloxane(s) may in principle contain any of the functional groups, which may be pendant and/or terminal, described above in connection with the initial coating as susceptible to polysiloxane curing. Interference with latency is no longer a consideration, however, so that, for example, there are not the same disadvantages arising from the presence of silanol groups, and the polysiloxane is advantageously curable by virtue of such groups. Additionally or alternatively, the polysiloxane may be curable by virtue of curable functional groups selected from aliphatic, aromatic and araliphatic ether, ester and oxime groups, which may be substituted or unsubstituted, or also trialkoxysilyl or hydrosilyl groups. A curable ether group may be, for example, an alkoxy group such as, for instance, methoxy or ethoxy. An example of a curable ester group is acetoxo.

Thus, by way of preferred example, a curable polysiloxane may be curable by virtue of oxime groups of the formula



in which R^4 and R^5 may be the same or different and each represents a straight-chain or branched, saturated or unsaturated, aliphatic hydrocarbon radical, preferably having up to 7 carbon atoms, more especially up to 4 carbon atoms, especially a methyl or ethyl group; an

aromatic group, for example, a phenyl group; or an
araliphatic group, for example, a benzyl group,
or R^4 and R^5 together represent an alkylene group, or one
of R^4 and R^5 represents hydrogen. A group R^4 and/or R^5
5 may be substituted or unsubstituted.

Oxime-functional polysiloxanes may be prepared by
reaction of the corresponding hydroxy-functional siloxane
with a ketiminoxysilane, for example, methyl tris(methyl-
ethylketiminoxy) silane, or one or more of the following
10 ketiminoxysilanes:

$\text{CH}_3\text{Si} [\text{ON} = \text{C}(\text{CH}_3)_2]_3$, $\text{CH}_3\text{Si} [\text{ON} = \text{C}(\text{CH}_3)\text{C}_2\text{H}_5]_3$,
 $(\text{CH}_2 = \text{CH})\text{Si} [\text{ON} = \text{C}(\text{CH}_3)\text{C}_2\text{H}_5]_3$, $\text{C}_6\text{H}_5\text{Si} [\text{ON} = \text{C}(\text{CH}_3)_2]_3$,
 $\text{CH}_3\text{Si} [\text{ON} = \text{C}(\text{C}_2\text{H}_5)(\text{CH}_2)_3\text{CH}_3]_3$,
 $(\text{CH}_3)_2\text{C} = \text{NOSi} [\text{ON} = \text{C}(\text{CH}_3)\text{C}_2\text{H}_5]_3$
15 $\text{CH}_3\text{Si} [\text{ON} = \text{C}(\text{CH}_2)_4]_3$,
 $\text{CH}_3\text{Si} [\text{ON} = \text{C}(\text{CH}_2)_5]_3$,
 $\text{Si}[\text{ON} = \text{C}(\text{C}_2\text{H}_5)(\text{CH}_3)]_4$ or $\text{Si}[\text{ON} = \text{C}(\text{CH}_3)_2]_4$.

Preferred polysiloxanes are linear polymers and
advantageously have the structure $\text{R}^3\text{O}(\text{SiR}^1\text{R}^2\text{O})_n\text{R}^3$,
20 in which R^1 and R^2 , which may be the same or different on
each silicon atom and on different silicon atoms in the
polymer, each represents an alkyl group such as, for
example, methyl, ethyl, or propyl; an alkenyl group such
as, for example, vinyl or allyl; a cycloalkyl or cyclo-
25 alkenyl group; an aryl group such as, for example,
phenyl; or a halogenated or cyano-substituted hydrocarbon
group, with the proviso that one of R^1 and R^2 may repre-
sent hydrogen on some or all of the silicon atoms and
that R^1 and R^2 may each represent hydrogen on some of the
30 silicon atoms,

OR^3 represents a curable functional group in which R^3
represents a monovalent radical such as, for example,
hydrogen, alkyl, aryl or $\text{R}^4\text{R}^5\text{CN}$ where R^4 and R^5 are as
hereinbefore defined, and
35 n represents a degree of polymerisation. Preferably R^1
and R^2 are each methyl, although partial or total

replacement of R^2 by phenyl may be of advantage.

It is generally advantageous for at least some and preferably all curable functional groups in the polysiloxane to be bonded directly to silicon.

5 The polysiloxane may have a number-average molecular weight in the range of from 1 500 to 310 000, generally from 1 800 to 80 000 or 85 000. Preferably, the number-average molecular weight is at least 5 000, advantageously at least 10 000, and more especially at least
10 15 000. The upper limit of molecular weight will usually be 60 000 or 70 000.

 The polysiloxane preferably has a viscosity in the range of from 7.5 to 200 poise at 25°C. By way of illustration, it will in general be desirable to utilise
15 a hydroxy-functional polysiloxane having a viscosity towards the upper end of the range, whereas for an oxime-functional polysiloxane it will in general be desirable to utilise a material having a viscosity towards the lower end of the range.

20 Advantageously, a curing catalyst is used to promote the reaction of the curable polysiloxane with the unreacted functional groups on the initial coating. Examples of catalysts which may be used include the carboxylic acid salts of various metals, for example,
25 tin, zinc, iron, lead, barium and zirconium. The salts are preferably salts of long-chain carboxylic acids, for example, dibutyltin dilaurate, dibutyltin dioctate, iron stearate, tin (II) octoate and lead octoate. Further examples of suitable catalysts include organobismuth and
30 organotitanium compounds and organo-phosphates such as bis(2-ethyl hexyl) hydrogen phosphate.

 Other possible catalysts include chelates such as, for example, dibutyltin acetoacetate.

 As a further possibility, the catalyst may comprise
35 a halogenated organic acid, which has at least one halogen substituent on a carbon atom which is in α -

position relative to the acid group, and/or at least one halogen substituent on a carbon atom which is in β -position relative to the acid group, or a derivative which is hydrolysable to form such an acid under the conditions of the condensation reaction.

Where appropriate in the following description, references to the acid catalyst include references to hydrolysable derivatives thereof.

The acid catalyst may be a mono-, di- or polybasic acid, but is preferably a monobasic acid.

The acid catalyst is a protonic acid and may comprise one or more carboxylic and/or sulphonic acid groups, preferably one or more carboxylic acid groups.

The or each halogen substituent may be fluorine, chlorine or bromine, but is preferably chlorine.

Advantageously, on an α - and/or a β -carbon atom of the acid catalyst, there are one or two fluorine substituents, from one to three chlorine substituents, or three bromine substituents. Thus, for example, the acid catalyst may comprise dichloroacetic acid, trichloroacetic acid or tribromoacetic acid.

The acid is advantageously an aliphatic acid, but may comprise one or more aromatic groups, such as phenyl or substituted phenyl, provided that there is preferably no aromatic group attached to the α -carbon atom or bonded directly to the acid group. An aromatic group may be a heterocyclic group, such as pyridyl or pyrrolyl. An aliphatic acid may be a cyclic or, preferably, an acyclic acid.

Advantageously, the catalyst is a halogenated alkanolic acid having up to 5 carbon atoms or a hydroxy-substituted derivative of such an acid.

As examples of acid derivatives which are hydrolysable to form the acids under the conditions of the condensation reaction there may be mentioned anhydrides, for instance, trichloroacetic acid anhydride, and esters,

which may be hydrocarbyl esters, especially methyl esters, or alkyl silyl esters, advantageously C₁₋₄ alkylsilyl esters, especially methylsilyl esters. Thus, for example, the catalyst may comprise trimethylsilyl-trichloroacetate.

If the catalyst contains more than one acid group, there may be halogen substitution on each α - and/or β -carbon atom or on only some of those carbon atoms.


The acid catalyst may carry one or more other substituents in addition to the specified halogen substitution.

The acid catalyst may be used alone or in conjunction with one or more other such catalysts but in the absence of any metal salt catalyst of the kind previously proposed. In particular, acid catalysts of the invention offer the possibility of dispensing with tin-based catalysts such as dibutyltin dilaurate.

The proportion of catalyst may be in the range of from 0.01 to 5% by weight, based on the amount of polymer (B), preferably at least 0.05% by weight and advantageously not exceeding 2% by weight.

It may be necessary or desirable to use a cross-linking agent for the curing reaction.


Advantageously, a cross-linking agent comprises a functional silane, more especially a functional silane of the formula



in which the groups represented by R¹ to R⁴ may be the same or different and, subject to there being at least di-functionality, each may comprise a straight-chain or branched, saturated or unsaturated, aliphatic hydrocarbon radical, preferably having up to 7 carbon atoms, more especially up to 4 carbon atoms, or an


aromatic or araliphatic hydrocarbon radical, such as, for example, phenyl or benzyl, or an aliphatic or aromatic other group, such as an alkoxy, phenoxy or benzyloxy group, or an ester group. An aliphatic group R^1 to R^4 is preferably an alkyl group, advantageously a C_1 - C_4 alkyl group, preferably a methyl or ethyl group, and an alkoxy group R^1 to R^4 is advantageously C_1 - C_4 alkoxy, preferably methoxy or ethoxy. Preferred examples of alkoxysilanes of the formula (I) include tetraalkyl orthosilicates such as tetramethyl, -ethyl, -propyl or -butyl orthosilicate, dimethoxydimethyl silane and diethoxydimethyl silane. It will be appreciated that, in order to serve as a cross-linking agent, a compound of formula (I) must be at least difunctional and preferably at least tri-functional. Any of the groups R^1 to R^4 in formula (I) may be unsubstituted or may be substituted by one or more substituents selected, for example, from halogen (especially chlorine or fluorine), amino groups or alkyl groups, which may themselves be substituted or unsubstituted.

Alternatively, a functional silane cross-linking agent may be reactive by virtue of one or more oxime groups of the formula



in which R^4 and R^5 may be the same or different and each represents a straight-chain or branched saturated or unsaturated, aliphatic hydrocarbon radical, preferably having up to 7 carbon atoms, more especially up to 4 carbon atoms, especially a methyl or ethyl group; an aromatic group, for example, a phenyl group; or an araliphatic group, for example, a benzyl group, or R^4 and R^5 together represent an alkylene group, or one of R^4 and R^5 represents hydrogen. A group R^4 and/or R^5 may be substituted or unsubstituted.

Thus, the functional silane may be a ketiminoxy-silane, for example, methyl tris(methylethylketiminoxy) silane, or one or more of the following ketiminoxy silanes:



Other possible cross-linking or curing agents include oximes such as vinyltris(methylethylketoxime) or methyltris(methylethylketoxime).

As a further possibility, more particularly when
 15 organometallic catalysts are used, especially tin-based catalysts, a cross-linking or curing agent may comprise a cyclic compound of the following formula:



in which n is an integer of from 3 to 10, and R represents hydrogen or methyl. Such materials are less
 25 preferred, however, because of the possibility of foaming arising from hydrogen evolution on curing.

A silane cross-linking agent may in principle be incorporated in a monomeric form or in the form of a self-condensation product, which may be, for example,
 30 a dimer, trimer, heptamer or a low molecular weight polymer.

The proportion of cross-linking agent may be in the range of from 0.05 to 10% by weight, generally from 2 to 5% by weight, based on the amount of polymer (B).

35 The process for forming the initial coating and for applying the subsequent layer of curable polysiloxane is

most conveniently carried out using a solution of the corresponding material in a non-reacting volatile solvent. Suitable solvents include aromatic hydrocarbons, for example toluene, xylene and trimethylbenzene; alcohols, for example, butanol; ketones, for example 4-methylpentan-2-one (methylisobutylketone), 5-methylhexan-2-one (methylisoamylketone) and cyclohexanone; esters, for example butyl acetate and 2-ethoxyethyl acetate, and mixtures of the above with one another or with an aliphatic hydrocarbon, for example in the form of white spirit. Such solutions can be applied to the surface to be coated by any of the known methods such as brush-painting, roller-painting, spray-painting and using aerosol formulations. In order to minimise the use of solvent on both cost and environmental grounds, it is advantageous to use as concentrated a solution as possible which is compatible with the coating technique employed. A solution of the coating composition comprising components (A) or (B), as the case may be, may comprise at least 35% by weight solids, generally at least 50% by weight solids. More concentrated solutions, for example containing at least 70% solids, may be employed if the polymer component (A) is of low molecular weight. In principle, the maximum solids content may be as high as 90% by weight or even more, but in general the maximum practicable solids content will be in the range 75-85% by weight, typically 80% by weight.

The presence of water is required in order to achieve full cure in the process of the invention, but specific addition of water is not normally required, either during or after application of the polysiloxane. It will in general be found that atmospheric moisture is sufficient to induce curing, and it will not normally be necessary or appropriate to heat the applied polysiloxane for curing purposes.

It is preferable to take steps to minimise the water content of all ingredients of the initial coating formulation and also the polysiloxane formulation, and it will be appreciated that no water or aqueous material should be added. Thus, for example, commercially available solvents will frequently contain a small amount of water (say, 1-2% by volume) and it is preferable to reduce the water content of such materials before use. In principle, such reduction in water content may be achieved by distillation in conjunction with a drying agent such as, for example, sodium, sodium hydride or calcium hydride or anhydrous calcium sulphate, but advantageously a reactive water-scavenger is used, for example, an inorganic salt such as, for example, magnesium sulphate (followed by filtration) or a mono- or di-functional silane, for instance, ethoxytrimethyl silane.

A coating composition comprising polymer (B) may include one or more unreactive oils such as, for example, a silicone oil, especially a methylphenyl silicone oil such as that sold by Rhone-Poulenc under the trademark "Rhodorsil Huile 550" or a petroleum or polyolefin oil or a polyaromatic oil. A preferred example is petrolatum oil.

The proportion of unreactive oil(s) may be in the range of from 5 to 25% by weight, based on the amount of component (B), preferably up to 10% by weight.

The initial coating may be a clear, transparent material or may be pigmented or dyed, provided that any pigment or dye used does not detract unduly from the desired latency (as a result, for example, of high moisture content or surface acidity or basicity). The pigment volume concentration in the coating formulation may typically be in the range of from 0.5 to 25%.

Particular mention may be made, for instance, of the use of metallic flake materials (for example, aluminium

flake) or other so-called barrier pigments; also anti-corrosive pigments.

5 The curable polysiloxane material may likewise be clear, pigmented or dyed, and either or both layers may incorporate other excipients and/or fillers such as barium sulphate or other mineral fillers, pyrogenic silica, bentonite or other clays.

10 Depending on reactivities, a coating formulation comprising the curable polysiloxane(s) can in principle be packaged in a one-, two or three-pack system. The initial coating formulation can be applied simply and easily as a one-pack system.

15 The thickness of the initial coating layer when dry may be in the range of from 50 to 100 microns, and the thickness of the layer comprising cured polysiloxane may be in the same range. More than one of each layer may be applied if desired.

20 The substrate can be any material that is to be used in a fouling, especially aquatic, environment. Thus, for example, the substrate may be metal, for instance, steel or aluminium; wood; concrete; a fibre-reinforced resin such as, for instance, a polyester resin; or another plastics material. A known anti-corrosive coating (such as, for instance, an epoxy, vinyl or alkyd coating) may be applied to the substrate before application of the initial coating formulation.

25 The initial layer applied in accordance with the invention can be formulated as a combined tie-coat and sealer.

30 A particular advantage of the invention is that the initial coating can be applied successfully over a range of worn or damaged anti-fouling coatings, especially if suitable barrier or anti-corrosive pigments are used, thereby avoiding a time-consuming and (in the case of toxic anti-fouling materials) potentially hazardous operation. In general, the only surface preparation

35

needed before application of an initial coating according to the invention is a high-pressure fresh water wash.

Examples of anti-fouling coatings to which an initial coating according to the invention can be applied include self-polishing tin copolymers, rosin Laroflex and rosin acrylic. Low surface-energy systems such as silicones and fluoropolymers do not provide a sound base on which to apply an initial coating according to the invention.

Further important advantages are that the sequential application of layers according to the process of the invention is a simpler, more flexible and more controllable procedure than is offered by complex systems designed to produce outer siloxane-rich regions (such as WO 93/13179).

By appropriate selection of various parameters as described herein, especially the nature and content of the functional groups providing latent reactivity, the initial layer composition in the process of the invention can be designed to permit a relatively long time interval between the application of the separate layers.

The following Examples illustrate the process of the invention:

Example 1

A glass-reinforced plastics (GRP) substrate bearing a coating of aged anti-fouling material (self-polishing tin copolymer, rosin Laroflex or rosin acrylic) is cleaned by high-pressure washing and allowed to dry.

A first coating formulation is applied to the washed substrate by brushing and roller-coating and allowed to dry to give an initial layer of average thickness 75 microns having latent reactivity by virtue of unreacted functional groups derived from the coating formulation.

Before exhaustion of the latency period provided by the unreacted functional groups, a second coating

formulation, comprising a curable organopolysiloxane, is applied to the initial layer and cured to give an adherent anti-fouling layer of average thickness 75 microns.

5 The composition of the first coating formulation is as follows:

	<u>Parts by weight:</u>
	Acrylic polymer A 54.7
	Xylene 7.5
10	Bentone 2.9
	Talc 16.7
	Black iron oxide 2.9
	Aluminium flake 13.0
	Methyl isobutyl ketone 2.3

15

 The latency period provided by the initial layer formed from this composition is determined in a preliminary experiment, in which test portions of the curable organopolysiloxane composition are applied at a series of different time intervals to different test areas of the initial layer. The latency period is taken to be the maximum time interval, under the prevailing conditions of temperature and humidity (after application of the initial layer) at which satisfactory
20 adhesion of the polysiloxane coating is still achieved.
25

Examples 2-8:

 The process of Example 1 is repeated using the different initial coating compositions set out below.
30 The same GRP substrate is used except where indicated.

Example 2:

	<u>Parts by weight</u>
	Acrylic polymer A 67.0
35	Xylene 10.1
	Bentone 1.6

	Talc	9.3
	Black iron oxide	1.6
	Aluminium flake	7.2
5	Methyl isobutyl ketone	3.2

Example 3:

		<u>Parts by weight</u>
	Acrylic polymer A	91.5
10	Xylene	8.5
	<u>Substrate:</u>	gel-coated GRP (no previous anti-fouling treatment), primed with an epoxy anti-corrosive composition.

15

Example 4:

		<u>Parts by weight</u>
	Acrylic polymer A	54.7
	Xylene	7.5
20	Bentone	2.9
	Talc	16.7
	Black iron oxide	2.9
	Aluminium flake	13.0
	Methyl isobutyl ketone	2.3

25

Example 5:

		<u>Parts by weight</u>
	Acrylic polymer B	67.0
	Xylene	10.1
30	Bentone	1.6
	Talc	9.3
	Black iron oxide	1.6
	Aluminium flake	7.2
	Methyl isobutyl ketone	3.2

35

Example 6:

		<u>Parts by weight</u>
	Acrylic polymer B	91.5
	Xylene	8.5
5	<u>Substrate:</u>	wood (no previous anti-fouling treatment), primed with an anti-fouling primer.

Example 7:

		<u>Parts by weight</u>
	Epikote 1001 Adduct	54.7
	Xylene	7.5
	Bentone	2.9
	Talc	16.7
15	Black iron oxide	2.9
	Aluminium flake	13.0
	Methyl isobutyl ketone	2.3

Example 8:

		<u>Parts by weight</u>
	Epikote 1001 Adduct	91.5
	Xylene	8.5
	<u>Substrate:</u>	bare concrete (no previous anti-fouling treatment), primed with an epoxy anti-corrosive composition.
25		

The acrylic polymer A used in the Examples is derived from the following monomers:

		<u>Parts by weight:</u>
	Methoxyethylacrylate	306.6
	Methylmethacrylate	715.3
	Trimethoxysilylpropylmethacrylate	283.2
35	Mercaptopropyltrimethoxy silane	56.0

The acrylic polymer A is prepared as follows:-

Trimethylbenzenes (540.0g) are added to a 3 litre flange-topped reaction vessel, fitted with mechanical stirrer, temperature probe, water condenser and feed inlet. A monomer feed is prepared, made up from monomers and radical initiator Azobis(isobutyronitrile) (AIBN, 23.4g). The reaction vessel is heated to 100°C under a slow stream of nitrogen and the feed added over a 3 hour period. During the addition, the temperature is maintained at ~ 100°C using a temperature control unit. Upon completion of the monomer feed, the solution is maintained at 100°C for 30 minutes after which time a boost of AIBN (7.8g) in trimethylbenzenes (30g) is added in one shot. After stirring the solution at 100°C for 45 minutes, a second identical boost is added and the solution stirred for a further 1 hour before being allowed to cool.

% Solids (Theor.)	=	70%
Tg (Theor.)	=	39.1°C
Molecular Weight (Mn)	~	3000

The acrylic polymer B used in the Examples is derived from the following monomers:

Parts by weight:

Butylacrylate	198.2
Methylmethacrylate	757.0
Triisopropoxysilylpropylmethacrylate	393.1

The acrylic polymer B is prepared analogously to acrylic polymer A, and has Tg (Theor.) = 36.7°C and molecular weight (Mn) ~ 10 000.

The epoxy adduct I used in the Examples is obtained from 966.2 parts by weight of Epikote 1001 (a condensation product of bisphenol A and epichlorohydrin) and 33.8 parts by weight of mercaptopropyltrimethoxysilane. The adduct is prepared by the following procedure:-

Ethanol (1000.0g) and Epikote 1001 are added via a wide neck funnel to a 3 litre flange-topped reaction vessel, fitted with mechanical stirrer, temperature probe and water condenser. A white emulsion is formed on stirring and heating to reflux (ca. 78°C). Mercaptopropyl-trimethoxy silane is then added drop-wise via a peristaltic pump over a period of 4 hours. After addition of the silane, the reaction is allowed to proceed at reflux for a further 1 hour, or until the reaction is complete as determined by ¹³C NMR.

The solution is allowed to cool to ca. 50°C and CB30 (428.0g) is added. The flask is fitted with still head and distillation take-off apparatus, and all the low boiling solvent (ethanol:methanol ca 85.15) removed at low temperature (still head ca. 40°C) under reduced pressure (ca. 600 mmHg).

% Solids (Theor.)	=	70%
Tg (Theor.)	=	38.9°C

An alternative epoxy adduct II may be obtained analogously from 900.0 parts by weight of Epikote 1004 (a condensation product of bisphenol A and epichlorhydrin) and 100.0 parts by weight of mercaptopropyl-dimethoxymethyl silane.

% Solids (Theor.)	=	60%
Tg (Theor.)	=	61.9°C

The latency period provided by acrylic polymer A and the epoxy adduct I is up to 7 days; the latency period provided by acrylic polymer B and the epoxy adduct II is up to 2 weeks.

Coating formulations for forming the second coating in the Examples are as follows:

a) One-pack formulation

Parts by weight

	α W-hydroxy functional dimethyl siloxane (viscosity 35 poise)	55.00
5	Methyltrimethoxy silane	2.50
	Airflow silica (Aerosil)	2.20
	Titanium ethylacetoacetate	1.00
	Trimethylbenzenes	29.40

10 b) Two-pack formulation

Parts by weight

Base

	α W-hydroxy functional dimethyl siloxane (viscosity 35 poise)	100.00
15	Air floated silica (Aerosil)	8.00
	Methyltris(methylethylketoxime)silane	6.00

Catalyst Solution

	Trimethylbenzenes	15.00
	Dibutyltindilaurate	0.08

20

c) Three-pack formulation

Parts by weight

Base

25	α W-hydroxy functional dimethyl siloxane (viscosity 35 poise)	56.00
	Air floated silica (Aerosil)	1.70
	Silicone oil (Rhodorsil RP550)	4.10
	Trimethylbenzenes	11.10

Curing agent

30	Tetraethylorthosilicate	2.60
	Silicone oil (Rhodorsil RP550)	0.80
	Trimethylbenzenes	8.50

Catalyst Solution

	Dibutyltindilaurate	0.55
35	Trimethylbenzenes	14.20


CLAIMS

1. A process for inhibiting the fouling of a substrate in a fouling environment, which comprises forming on the substrate, before exposure to the said environment, a coating comprising a film-forming polymer (A) carrying unreacted curable silicon-containing functional groups providing latent reactivity, and thereafter applying a layer comprising a curable polysiloxane (B) and bonding the applied layer to the said coating by a condensation curing reaction involving the unreacted functional groups thereon.

2. A process as claimed in claim 1 wherein the curable silicon-containing functional groups of (A) are pendant functional groups.


3. A process as claimed in claim 1 or 2, wherein the silicon-containing functional groups are curable by virtue of one or more curable functional groups selected from aliphatic, aromatic and araliphatic ether and oxime groups, which groups may be substituted or unsubstituted.

4. A process as claimed in claim 1 or claim 2, wherein the curable silicon-containing functional groups are groups of the formula



in which the groups represented by R_1 , R_2 and R_3 may be the same or different and each may comprise an ether or ester group, preferably a group including a straight-chain or branched alkyl moiety having from 1 to 4 carbon atoms, and in which one or two of R_1 to R_3 may represent hydrogen or a hydrocarbon group, preferably a straight-chain or branched alkyl group having from 1 to 4 carbon atoms.

5. A process as claimed in claim 1 or claim 2, wherein the silicon-containing functional groups are curable by virtue of one or more oxime groups of the formula



in which R⁴ and R⁵ may be the same or different and each represents a straight-chain or branched, saturated or unsaturated, aliphatic hydrocarbon radical, preferably having up to 7 carbon atoms, more especially up to 4 carbon atoms, especially a methyl or ethyl group; an aromatic group, for example, a phenyl group; or an araliphatic group, for example, a benzyl group; or R⁴ and R⁵ together represent an alkylene group; or one of R⁴ and R⁵ represents hydrogen.

6. A process as claimed in claim 1 or claim 2, wherein the curable silicon-containing functional groups are trimethoxy silyl or methyl dimethoxysilyl groups.

7. A process as claimed in any one of claims 1 to 6, wherein the polymer (A) has no silanol or amine functionality.

8. A process as claimed in any one of claims 1 to 7, wherein the polymer (A) carries no functional groups other than the curable silicon-containing functional groups conferring latent reactivity.

9. A process as claimed in any one of claims 1 to 8, wherein the polymer (A) is substantially free from siloxane repeating units.

10. A process as claimed in any one of claims 1 to 9, wherein the polymer (A) is derived from one or more monomers (A1) which carry curable silicon-containing functional groups and one or more monomers (A2) which do not carry such groups.

11. A process as claimed in any one of claims 1 to 10, wherein the polymer (A) is derived from one or more ethylenically unsaturated monomers.

12. A process as claimed in any one of claims 1 to 11, wherein the T_g of the polymer (A) is above ambient temperature.

13. A process as claimed in any one of claims 1 to 12, wherein the polymer (A) has a number-average molecular weight in the range of from 3 000 to 10 000.

14. A process as claimed in any one of claims 1 to 13, wherein the unreacted curable silicon-containing functional groups provide a period of latent reactivity of 48 hours or more.

15. A process as claimed in any one of claims 1 to 14, wherein the polysiloxane (B) is curable by virtue of silanol or silicon-alkoxy groups.

16. A process as claimed in any one of claims 1 to 14, wherein the polysiloxane (B) is curable by virtue of curable functional groups selected from aliphatic, aromatic and araliphatic ether, ester and oxime groups, trialkoxysilyl or hydrosilyl groups.

17. A process as claimed in any one of claims 1 to 16, wherein the polysiloxane (B) is a linear polymer.

18. A process as claimed in claim 17, wherein the polysiloxane (B) has the structure $R^3O(SiR^1R^2O)_nR^3$, in which R^1 and R^2 , which may be the same or different on each silicon atom and on different silicon atoms in the polymer, each represents an alkyl group; an alkenyl group; a cycloalkyl or cycloalkenyl group; an aryl group; or a halogenated or cyano-substituted hydrocarbon group, with the proviso that one of R^1 and R^2 may represent hydrogen on some or all of the silicon atoms and that R^1 and R^2 may each represent hydrogen on some of the silicon atoms, OR^3 represents a curable functional group in which R^3 represents a monovalent radical; and n represents a degree of polymerisation.

19. A process as claimed in any one of claims 1 to 18, wherein the polysiloxane (B) has a number-average molecular weight in the range of from 5 000 to 85 000.

20. A process as claimed in any one of claims 1 to 19, wherein the polysiloxane (B) is applied in

admixture or conjunction with a catalyst for the condensation curing reaction.

21. A process as claimed in any one of claims 1 to 20, wherein the polysiloxane (B) is applied in admixture or conjunction with a cross-linking agent for the condensation curing reaction.

22. A process as claimed in any one of claims 1 to 21, wherein the substrate has a worn or damaged anti-fouling coating thereon.

23. A process as claimed in any one of claims 1 to 22, wherein the fouling environment is an aquatic environment.

24. A process as claimed in claim 23, wherein the fouling environment is a marine environment.

25. A substrate in a fouling environment and bearing a coating and a cured polysiloxane layer thereon, formed by a process as defined in any one of claims 1 to 24.

ABSTRACT

FOULING INHIBITION

5

10

15

A process for inhibiting the fouling of a substrate in a fouling environment, which comprises forming on the substrate, before exposure to the said environment, a coating comprising a film-forming polymer (A) carrying unreacted curable silicon-containing functional groups providing latent reactivity, and thereafter applying a layer comprising a curable polysiloxane (B) and bonding the applied layer to the said coating by a condensation curing reaction involving the unreacted functional groups thereon.

20

The initial coating can be applied over a range of worn or damaged anti-fouling coatings. The sequential application of layers is a simpler, more flexible and more controllable procedure than is offered by complex systems designed to produce outer siloxane-rich regions. Relatively long latency periods are achievable.

